

Cover grade characteristics and applications	Physical Properties							
	Standard	Before Ageing		Temperature of ageing *C	Duration of ageing hrs	After Ageing		Max abrasion loss MM3
Tensile strength MPA		Elongation %	Change in elongation %					
<b>HYGIENIC CONVEYOR BELT</b>								
This cover grade is specially designed with non-toxic rubber compounds for use in the food processing pharmaceutical industry	IS 1891 Part-IV	10	350	70	72	-10	-10	Not specified
						-20	-45	