

Characteristics and Applications	Physical Properties							
	Standard	Before Ageing		Temperature of ageing *C	Duration of ageing hrs	After Ageing		Max abrasion loss MM3
		Tensile strength MPA	Elongation %			Change in elongation %		
OIL RESISTANT BELT								
Composed of Synthetic rubber compounds, this grade is resistant to mineral, vegetable, animal oils and fats	IS 1891 Part - I	12	250	70	72	-35	-35	Not specified